




## Hammer Crusher

### Usage:

This series of crusher is applicable for crushing of brittle minerals, such as coal, salt, plaster, alum, brick, tile and limestone with compression strength no more than 100mpa and humidity no more than 15%.



### Main technical parameter of hammer crusher

Type	Specifications	Feeding size(mm)	Discharging size (mm)	Throughput (m <sup>3</sup> /h)	Motor		Total weight(t)	Dimensions (L*W*H)(mm)
					Electricity	Power (kw)		
Hammer crusher	PCΦ400*300	≤200	≤25	5-10	4	11	0.8	900*670*860
	PCΦ600*400	≤250	≤30	10-22	4	22	1.5	1200*1050*1200
	PCΦ800*600	≤250	≤25	18-40	4	55	3.2	1310*1180*1310
	PCΦ1000*800	≤350	≤35	25-50	4	75	4.3	1600*1390*1575
	PCΦ1000*1000	≤300	≤35	30-55	6	132	8	1800*1590*1775
	PCΦ1250*1250	≤350	≤35	35-65	6	180	14	2060*1600*1890
	PCΦ1400*1400	≤350	≤35	50-100	6	280	32	2365*1870*2220
	PCΦ1600*1600	≤350	≤35	100-150	8	480	37.5	3050*2850*2800